



www.ecorubberedenvale.co.za  
 sales@ecorubberedenvale.co.za

## ECO INSULATE INFO SHEET

<b>PRODUCT DESCRIPTION</b>	<ul style="list-style-type: none"> <li>* Eco Insulate is a Thermal insulative barrier coating formulated on an elastomeric polymer base.</li> <li>* This water-borne coating boasts cutting-edge technology with the addition of glass microspheres.</li> <li>* Eco Insulate provides superior adhesion that has been proven resistant to weathering, chalking and cracking.</li> <li>* This product creates a thermal barrier that is UV reflective and which limits thermal conductivity.</li> <li>* The external coating significantly reduces the interior temperatures of facilities, resulting in lower mechanical cooling requirements.</li> </ul>
----------------------------	---

<b>PRODUCT BENEFITS</b>	<ul style="list-style-type: none"> <li>* Improves life span of substrates.</li> <li>* Thermal insulation reduces cooling costs</li> <li>* Corrosion control</li> <li>* Encapsulation (Asbestos)</li> <li>* Highly stretchable and contracts to its original form. Therefore withstands thermal cycling.</li> <li>* No solvents. Therefore it is Environmentally Friendly and can be applied where rainwater is harvested.</li> <li>* No negative effect on human or animal life.</li> <li>* Significant waterproofing ability (No ponding longer than 48 hours)</li> <li>* Can be applied to all construction materials including shipping containers.</li> <li>* Spray, paint or roller applied</li> </ul>
-------------------------	---

<b>THERMAL REDUCTION BENEFIT</b>	<ul style="list-style-type: none"> <li>* Metal Sheeted Areas</li> </ul> <table border="1" style="margin-left: 20px; margin-bottom: 10px;"> <thead> <tr> <th style="text-align: center;">Ambient Temp °C</th> <th style="text-align: center;">Reduction %</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">18°C</td> <td style="text-align: center;">7</td> </tr> <tr> <td style="text-align: center;">25°C</td> <td style="text-align: center;">27</td> </tr> <tr> <td style="text-align: center;">36°C</td> <td style="text-align: center;">37</td> </tr> <tr> <td style="text-align: center;">45°C</td> <td style="text-align: center;">43</td> </tr> </tbody> </table> <ul style="list-style-type: none"> <li>* Lower temperature losses were recorded where exterior ambient temperatures fell below 8°C</li> <li>* The product therefore creates a more livable environment and reduces the need for heating.</li> <li>* More significant reduction in temperature are experienced where substrate temperatures are recorded on coated and non-coated areas.</li> </ul>	Ambient Temp °C	Reduction %	18°C	7	25°C	27	36°C	37	45°C	43
Ambient Temp °C	Reduction %										
18°C	7										
25°C	27										
36°C	37										
45°C	43										

## TECHNICAL DATA

PARAMETER	Pure Acrylic
FINISH	Homogeneous: smooth, white
SELF PRIMER	Positive
PH	8.68
VISCOSITY	128ku
SPECIFIC GRAVITY	0.9522
TOXICITY	Material is non-toxic & requires no special ventilation during application. Contains no materials considered to be hazardous to health.
FLAMMABILITY	Non-flammable. Does not support flame spread
PACKAGE STABILITY	One year + after opening: no settling or other undesirable effects. Materials completely dispersed after stirring.
ABRASION RESISTANCE	Medium to High
ELONGATION	70% with a 100% full memory
FUNGUS RESISTANCE	No fungus growth when material was tested in an environment in which three organisms were present.
V.O.C	78 grams per Litre
WATER %	26%
SOLIDS BY MASS	50%

## STANDARD PACKAGING

PACKAGING	20 Litres
-----------	-----------

## MATERIAL APPLICATION

SURFACE PREPARATION	* Surfaces to be sprayed / painted must be cleaned thoroughly and allowed to dry. They must be free from dirt, grease and other foreign matter. * Avoid application when the moisture is above 15% * Remove all unstable paint film. * Repair defective surfaces before application.
MATERIAL	Single component, ready-to-use from container with little stirring required.
APPROXIMATE COVERAGE	1 Litre per square meter
APPLICATION TEMPERATURE RANGE	Above 10°C
RECOATING	Excellent
PRIMARY CURE	3 hours at 25°C
FINAL CURE TIME	3 - 5 Days
AIRLESS SPRAY	Pressure : 1600 - 1700 psi; 110 - 117 bar

## HEALTH & SAFETY

SAFETY PRECAUTIONS	* Keep container tightly closed and keep out of reach of children and away from food and drink. * In case of contact with eye, rinse with water immediately and seek medical advice. * Remove splashes from skin by using soap and water. * Always keep container in a secure, upright position. * Dispose of any paint waste in accordance with the appropriate EHS Regulations
--------------------	--

NOTE: We warrant only the quality of our product. The data sheet is based on results obtained from experience and tests.

We reserve the right to change data without prior notice.